


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : F16L 9/12	A1	(11) International Publication Number: WO 99/49254 (43) International Publication Date: 30 September 1999 (30.09.99)
(21) International Application Number: PCT/SE99/00429 (22) International Filing Date: 18 March 1999 (18.03.99) (30) Priority Data: 9800967-3 23 March 1998 (23.03.98) SE (71) Applicant (for all designated States except US): WIRSBO BRUKS AB [SE/SE]; S-730 61 Virsbo (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): JOHANSSON, Bengt [SE/SE]; Vallingatan 3A, S-722 16 Västerås (SE). LUN- DEQUIST, Yngve [SE/SE]; Enebbavägen 12, S-730 61 Virsbo (SE). ASPLUND, Rauno [SE/SE]; Trädgårdsgatan 5, S-730 61 Virsbo (SE). (74) Agent: DR. LUDWIG BRANN PATENTBYRÅ AB; P.O. Box 171 92, S-104 62 Stockholm (SE).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i> <i>In English translation (filed in Swedish).</i>
(54) Title: MULTILAYER PLASTIC PIPE AND ITS USE (57) Abstract <p>The invention relates to a multilayer plastic pipe (1), preferably for use in heating systems. The multilayer pipe comprises an inner core (2) and a barrier layer (6) surrounding the core and preventing oxygen diffusion through the multilayered pipe. The core (2) is made of a material having viscoelastic properties, preferably cross-linked polyethylene, and the barrier layer (6) is surrounded by an outer layer (8) of a material having adhesive properties. The invention also relates to the use of a multilayer pipe for providing pipe couplings.</p> 		




FIG 1




FIG 2




FIG 3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 99/00429

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: F16L 9/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0030091 A2 (WIRSBØ BRUKS AKTIEBOLAG), 10 June 1981 (10.06.81), page 7, line 1 - line 9, figures 1,2 --	1,2
A	SE 500665 C2 (WIRSBØ BRUKS AB), 1 August 1994 (01.08.94), figure 1 --	8
A	DE 3104161 A1 (SIEMENS AG), 19 August 1982 (19.08.82) --	
A	DE 3319515 A1 (KABELMETAL ELECTRO GMBH), 29 November 1984 (29.11.84) -- -----	

☐ Further documents are listed in the continuation of Box C.
 ☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

15 June 1999

Date of mailing of the international search report

23-07-1999

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Axel Lindhult

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/06/99

International application No.

PCT/SE 99/00429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0030091 A2	10/06/81	SE 0030091 T3 AT 18292 T CA 1145272 A DK 504080 A FI 72680 B,C FI 803630 A GR 70044 A JP 56127441 A US 4614208 A	15/03/86 26/04/83 29/05/81 31/03/87 29/05/81 26/07/82 06/10/81 30/09/86
SE 500665 C2	01/08/94	AT 170272 T AU 690094 B AU 6047194 A CA 2155510 A DE 69412792 D,T EP 0682758 A,B ES 2122239 T FI 953670 A JP 8506407 T NO 953055 A NZ 261640 A PL 173682 B PL 309914 A SE 9300365 A WO 9418486 A	15/09/98 23/04/98 29/08/94 18/08/94 21/01/99 22/11/95 16/12/98 01/08/95 09/07/96 04/10/95 26/05/97 30/04/98 13/11/95 01/08/94 18/08/94
DE 3104161 A1	19/08/82	NONE	
DE 3319515 A1	29/11/84	NONE	

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

MULTILAYER PLASTIC PIPE AND ITS USE**FIELD OF THE INVENTION**

5 The present invention relates to a multilayer plastic pipe, preferably intended for water piping in central heating systems. The multilayer pipe comprises an inner core and an outer barrier layer which is surrounding the inner core and is made of a material which prevents oxygen diffusion through
10 the multilayered pipe. The invention also relates to the use of a multilayer plastic pipe.

BACKGROUND OF THE INVENTION

Plastic pipes have previously been used, for example,
15 for water distribution. Such pipes are preferably made of polyolefins, such as cross-linked polyethylene (PEX), polypropene or polybutylene. Plastic pipes which are to be used for water distribution in heating systems, such as for example, those for floor heating or for radiator systems, must be
20 provided with an oxygen barrier layer so as to prevent oxygen diffusion into the water and thus causing corrosion on the metal components which are part of the heating systems.

In order to prevent oxygen diffusion through the pipe, it is a commonly used method to coat the outer surface of the
25 pipe with a barrier layer of a material which prevents diffusion, such as for example, ethylene vinyl alcohol (EVOH). An intermediate layer of an adhesive material, an adhesive layer, may be provided between the inner core and the barrier layer, said intermediate layer being effective to create or
30 to increase the adhesion between the inner core, such as a PEX-pipe, and the outer barrier layer.

An advantageous technique for connecting plastic pipes with different types of couplings and fittings in water distribution systems is previously known, i.a. from SE-C2-500665
35 and SE-C2-501555. The described technique is used for pipe couplings for plastic pipes having viscoelastic properties, or memory properties, i.e. plastic pipes having a tendency to automatically shrink back to their original shape after, for

- 2 -

instance, an expansion. A pipe material having this property is, for example, cross-linked polyolefin, especially cross-linked polyethylene (PEX). The mechanical properties of the material allows a deformation of the pipe at temperatures as low as at least -20°C. In order to mount the plastic pipe on the pipe coupling, the end of the plastic pipe is expanded and a nipple is inserted into the expanded end of the pipe and is kept in the pipe until the pipe end shrinks back over the nipple. This known technique is advantageous as it is quick and easy to preform and provides a safe and water-tight coupling.

In accordance with the technique described above, the pipes are substantially expanded in a radial direction. This has proven to function very satisfactorily when PEX-pipes are being used. However, this advantageous coupling technique is disadvantageous when it is used on pipes having an oxygen barrier layer as described above. In the process of an substantial, radial expansion of the pipe, cracks may appear in the outer barrier layer, said cracks occurring especially at low temperatures, such as temperatures below about 15°C. The cracks which occur in the barrier layer have shown a tendency to propagate into the pipe wall during the expansion process of the pipe, thus causing pipe fractures leading to leaking pipe couplings.

Attempts have been made to solve the above problem by modifying known barrier materials. The object has been to try to find modified barrier materials which may withstand an expansion without cracking. So far, a modified barrier material which provides an acceptable solution to the expansion cracking problem has not been found.

SUMMARY OF THE INVENTION

The object of the present invention is thus to provide a solution to the above problem, in that the advantageous coupling technique may be used on the plastic pipes which are specially made for use in heating systems.

- 3 -

This object has been achieved according to the invention by means of a multilayer plastic pipe having the characterizing features as defined in the claims.

The inventive solution provides the advantage that the
5 advantageous coupling technique, which is quick, efficient and inexpensive, may be applied to a whole range of different pipes. This means that plumbers working with installations at the site do not require different couplings for different types of pipes, but may instead use just one type of couplings.

10 According to the invention the problem has been solved by coating the plastic multilayer pipe with an additional layer of an adhesive material, an adhesive layer. The adhesive layer may consist of the same or similar material as the intermediate adhesive layer which is applied between the
15 inner core and the barrier layer so as to increase the adhesion between the layers. The inventive multilayer pipe which is coated with an outer adhesive layer can be radially expanded without crack formation occurring in the barrier layer or in other parts of the pipe wall.

20 In a plastic pipe having an outer layer, such as a barrier layer, stress concentrations naturally occur especially in the outer layer, when the pipe is expanded. Therefore, stress cracks appear mainly in the outer layer and these cracks may propagate, as described above, into the pipe wall
25 during the expansion of the pipe and cause pipe fractures. According to the invention the outer barrier layer is coated with an additional layer which in itself is sufficiently pliable to absorb stress concentrations and which also adheres to the brittle barrier layer such that this layer is
30 "supported". This prevents or reduces the tendency to form cracks in the pipe wall.

The mechanical properties of crystalline materials, and also of semi-crystalline materials such as for example EVOH, depend among other things upon the crystalline structure of
35 the material. The crystalline structure is dependent upon the rate of crystallisation, i.e. the cooling rate. On extrusion of a plastic pipe with a barrier layer, the outer layer is

- 4 -

exposed directly to ambient air outside the extruder die. An extruded pipe with no additional outer layer is subjected to rapid cooling and crystallisation. On extrusion of a pipe having an outer adhesive layer according to the invention, the cooling of the barrier layer is slower and the thus obtained crystalline structure of said barrier layer has improved mechanical properties.

The barrier layer of a pipe with no additional outer layer is directly exposed to air when it leaves the extruder die at a temperature of above 200°C. An oxidative degradation of the barrier layer takes place at this stage which deteriorates the mechanical properties of the material. In a pipe coated with an additional layer outside the barrier layer according to the invention, the outer layer protects the barrier layer against said degradation during the cooling period and therefor the mechanical properties of the barrier layer is improved.

BRIEF DESCRIPTION OF THE DRAWING

The invention is described in more detail below with reference to the accompanying drawing showing by way of example a preferred embodiment of the invention.

Figure 1 is a cross-sectional view of a multilayer pipe according to the invention;
Figure 2 is an axial cross-section of an expanded multilayer pipe according to Figure 1 with an inserted nipple; and
Figure 3 shows the multilayer pipe according to Figure 2 which shrinks over the nipple.

DETAILED DESCRIPTION OF THE INVENTION

Figure 1 illustrates a cross-section of a preferred embodiment of a multilayer plastic pipe in accordance with the invention. The multilayer pipe 1 comprises an inner core 2 which is made of cross-linked polyolefin, preferably a cross-linked polyethylene, a PEX-pipe. The inner core 2 is made of a material having viscoelastic or memory properties, i.e. a

- 5 -

material which after expansion tends automatically to retain to its original shape.

A barrier layer 6 is arranged on the outside of the inner core 2 in order to prevent oxygen diffusion through the pipe 1. The material of the barrier layer 6 is preferably ethylene vinyl alcohol (EVOH), which is a material which is commonly used as an oxygen barrier. Different modified variants of EVOH may also be used as barrier layers. Other known barrier materials preventing oxygen diffusion through the pipe may also be used as barrier layer within the scope of the invention.

The barrier layer 6 is arranged outside the inner core 2, preferably and in the embodiment of Figures 1-3, with an intermediate layer 4 between the barrier layer 6 and the inner core 2 of an adhesive material, an adhesive layer. The intermediate adhesive layer 4 is arranged in order to create or improve the adhesion between the inner core 2 and the barrier layer 6 of the multilayer pipe. The material of the adhesive layer may be any of the well know and easily available products on the market having the property to adhere to the materials of the inner core 2 and the barrier layer 6. The material of the adhesive layer is preferably a modified polyethylene, such as for example a maleic anhydride modified polyethylene.

According to the invention, an additional layer 8 is arranged on the outside of the barrier layer 6. The outer layer 8 is an adhesive layer of the same or similar material to that of the intermediate adhesive layer 4 between the inner core 2 and the barrier layer 6. Within the scope of the invention, the material of the intermediate adhesive layer 4 and the outer adhesive layer 6, respectively, may of course consist of completely different materials having adhesive properties.

In accordance with a preferred embodiment of the invention, the wall thickness of the inner core 2 is about 1,5-25 mm, preferably about 1,8-5 mm, whilst the three outer layers 4, 6, 8 are relatively thin and have similar wall

- 6 -

thicknesses. According to the preferred embodiment, the intermediate adhesive layer 4 has a wall thickness of about 25-250 μm , preferably 50-100 μm , and the surrounding barrier layer 6 has a wall thickness of about 25-250 μm , preferably 50-125 μm . According to the preferred embodiment, the thickness of the outer adhesive layer 8 is about 25-250 μm , preferably 50-100 μm .

Figure 2 illustrates an axial cross-section of the multilayer pipe 1 according to Figure 1. The end part 10 of the pipe 1 has been expanded by an expander tool, which is not shown. A pipe coupling or a nipple 12, for example made of metal or plastic, is partly inserted into the expanded end 10 of the pipe.

An external lock ring, not shown, of elastic material, e.g. of the same material as the inner core, may be arranged on the outside of the end part 10 of the pipe as a reinforcement and may be expanded together with said end part 10.

Figure 3 illustrates how the expanded end part 10 of the pipe 1 tends to resume its original shape and shrinks onto the nipple 12. The pipe end 10 shrinks quickly and without external influence thus providing a safe and tight joint between the inside of the pipe end 10 and the outside of the inserted part of the nipple 12.

The multilayer pipe 1 has a flexible outer layer 8 which adhere to the brittle barrier layer 6. The pipe end 10 may therefor be exposed to a rapid and substantial radial extension, as illustrated in Figure 2, without crack formation or propagation occurring in any of the outer layers or in other parts of the multi-layer pipe.

It will be understood that the invention is not restricted to the aforescribed and illustrated embodiment and that several modifications are conceivable within the scope of the following claims. In the illustrated embodiment a barrier layer is surrounded by an inner and an outer adhesive layer, respectively. It is understood, however, that the inner adhesive layer 4 may be omitted or optionally replaced by

- 7 -

a modified barrier layer having properties which compensates the properties of the intermediate adhesive layer.

- 8 -

CLAIMS

1. A multilayer plastic pipe, preferably for use in heating systems and comprising an inner core (2) and a barrier layer
5 (6) surrounding the inner core and preventing oxygen diffusion through the multilayer pipe, **characterized** in that the core (2) is made of a material having viscoelastic properties, preferably cross-linked polyethylene, and that the barrier layer (6) is surrounded by an outer layer (8) made of a
10 material having adhesive properties.
2. A multilayer pipe in accordance with claim 1,
characterized in that an intermediate layer (4) of an adhesive material is arranged between the inner core (2) and the
15 barrier layer (6).
3. A multilayer pipe in accordance with any of claims 1-2,
characterized in that the material of the barrier layer (6) is ethylene vinyl alcohol.
20
4. A multilayer pipe in accordance with any of claims 1-2,
characterized in that the material of the barrier layer (6) is a modified ethylene vinyl alcohol.
- 25 5. A multilayer pipe in accordance with any of claims 1-4,
characterized in that the adhesive material is a modified polyethylene.
6. A multilayer pipe in accordance with any of claims 1-5,
30 **characterized** in that the wall thickness of the inner core (2) is 1,5-25 mm, preferably 1,8-5 mm, that the wall thickness of the barrier layer (6) is 25-250 μm , preferably 50-125 μm , and that the wall thickness of the outer adhesive layer (8) is 25-250 μm , preferably 50-100 μm .

35

- 9 -

7. A multilayer pipe in accordance with any of claims 2-6, **characterized** in that the wall thickness of the intermediate adhesive layer (4) is 25-250 μm , preferably 50-100 μm .
- 5 8. Use of a multilayer plastic pipe, which comprises an inner core (2) and a barrier layer (6) surrounding the inner core and preventing oxygen diffusion through the multilayer pipe, for providing a pipe coupling by radial expansion and subsequent shrinking of the pipe onto a nipple (12).
- 10 9. Use in accordance with claim 8, **characterized** in that the multilayer pipe (1) is provided with an outer layer (8) of an adhesive material on the barrier layer (6).
- 15 10. Use in accordance with claim 9, **characterized** in that the multilayer pipe (1) is provided with an intermediate layer (4) of an adhesive material between the inner core (2) and the barrier layer (6).